



národní
úložiště
šedé
literatury

Hydrodesulfurization CoMo/Al₂O₃ and CoMo/C Catalysts Prepared with Nitrilotriacetic Acid without Use of NH₄OH

Kaluža, Luděk
2014

Dostupný z <http://www.nusl.cz/ntk/nusl-175000>

Dílo je chráněno podle autorského zákona č. 121/2000 Sb.

Tento dokument byl stažen z Národního úložiště šedé literatury (NUŠL).

Datum stažení: 27.09.2024

Další dokumenty můžete najít prostřednictvím vyhledávacího rozhraní nusl.cz .

Hydrodesulfurization CoMo/Al₂O₃ and CoMo/C catalysts prepared with nitrilotriacetic acid without use of NH₄OH

L. Kaluža, Z. Vít, M. Zdražil

Institute of Chemical Process Fundamentals of the ASCR, v.v.i., Prague, Rozvojová 135, 165 02, Czech Republic, tel. +420 220390270, e-mail: kaluza@icpf.cas.cz.

The CoMo/Al₂O₃ catalyst modified with nitrilotriacetic acid (NTA catalyst) was prepared by the common procedure, well known in the literature, using excess of NH₄OH in the impregnation solution. The using of NH₄OH was believed indispensable in the literature, because NTA is insoluble in water (pH of its slurry in water is 2.1) and it is only little soluble at pH of 5-7 (pH of Co(NO₃)₂ solution is about 5.5 and pH of (NH₄)₆Mo₇O₂₄ solution is about 6). Just as in the literature, the catalyst was not calcined before sulfidation. Its activity in HDS of thiophene (TH) was measured at increased pressure of 1.0 MPa and temperature of 400 °C. The positive NTA effect of 1.37 (ratio of activities with and without NTA) falls into the range of 0.75-2.62 reported by previous authors, who tested the catalysts in TH HDS at atmospheric pressure.

The impregnation solution for NTA catalysts was then newly prepared without NH₄OH. Practically insoluble CoCO₃.xH₂O (pH of its slurry in water is 8.3) was used instead of usual, well soluble Co(NO₃)₂.6H₂O. It was found that the two separately insoluble compounds NTA and CoCO₃.xH₂O easily dissolved in joint aqueous slurry forming well soluble Co-NTA complex (CO₂ was released from the slurry). (NH₄)₆Mo₇O₂₄ was added and the impregnation solution containing all three components, NTA, Co and Mo, was obtained. Its pH was 2.3-3.8, depending on the molar NTA/Mo ratio, which was 1.0-3.2. The NTA CoMo/Al₂O₃ prepared with this solution (NTA/Mo=1.2) exhibited NTA effect of 1.54, which was reliably higher than the value of 1.37 mentioned above. Similar behaviour was observed for CoMo/C catalysts ("C" is for active carbon); the NTA effect was 1.23 and 1.36 with and without NH₄OH, respectively. It was concluded that the use of large amount of volatile, corrosive and toxic NH₄OH is at all not needed.

The positive NTA effect was also found for promoter free Mo/Al₂O₃ and Mo/C catalysts without NH₄OH; the values were 1.24 and 1.19, respectively. The positive NTA effect vanished in calcined NTA catalysts Mo/Al₂O₃ and CoMo/Al₂O₃, independently whether NH₄OH was used or not.

We have calculated and experimentally confirmed that in the catalysts without NTA before sulfidation, the deposited phase takes up only about 5% of the pore volume of Al₂O₃ support. The deposited Co-Mo-O phase forms a monolayer and all Co-Mo-species are in physical and chemical contact with the support surface. In NTA catalysts before sulfidation, the deposited NTA-Co-Mo phase takes up about 60% of the pore volume of Al₂O₃. During sulfidation, the metal-support interaction of the majority of the Co and Mo species is blocked not only "chemically" by their own NTA ligands, but also "physically" by the surrounding supported solid. The majority of deposited solid in dried NTA catalysts is sulfided as if it were in the unsupported form. This leads to different morphology and structure of Co-Mo sulfides as compared with the catalysts without NTA. It was concluded that the overall NTA action is a combination of not only "chemical" effects described in the literature (NTA blocks metal-support and metal-metal interactions, it influences supported phase morphology, it delays sulfidation of promoter, etc.), but also of the above "physical" effect.

The authors gratefully acknowledge the financial support of the Czech Science Foundation (grant no. P106/11/0902).