



národní  
úložiště  
šedé  
literatury

## **Catalytic Oxidation of Volatile Organic Compounds over Ceria-zirconia Supported Noble Metal Catalysts**

Topka, Pavel  
2014

Dostupný z <http://www.nusl.cz/ntk/nusl-175703>

Dílo je chráněno podle autorského zákona č. 121/2000 Sb.

Tento dokument byl stažen z Národního úložiště šedé literatury (NUŠL).

Datum stažení: 02.10.2024

Další dokumenty můžete najít prostřednictvím vyhledávacího rozhraní [nusl.cz](http://nusl.cz) .

## Catalytic oxidation of volatile organic compounds over ceria-zirconia supported noble metal catalysts

Pavel Topka\*, Luděk Kaluža

*Institute of Chemical Process Fundamentals of the ASCR, Rozvojová 2, Praha 6, CZ 165 02, Czech Republic*

\* corresponding author: [topka@icpf.cas.cz](mailto:topka@icpf.cas.cz)

### Abstract

Catalytic oxidation is a green and efficient way to handle man-made emissions of volatile organic compounds (VOC), which represent serious environmental issue. Despite high purchasing costs, supported noble metal catalysts are favored over metal oxides due to their high activity and selectivity, excellent stability and superior resistance against poisoning. In the present work, ceria-zirconia mixed oxide was employed as a support for gold and platinum catalysts that were characterized and tested in the gas-phase oxidation of model VOCs to investigate the influence of noble metal loading and type on the catalytic performance and selectivity of the catalysts. In the oxidation of dichloromethane, the noble metal catalysts showed lower catalytic performance than the parent  $\text{Ce}_{0.5}\text{Zr}_{0.5}\text{O}_2$  due to lower amount of acid sites that act as chemisorption sites for chlorinated compounds. However, platinum catalysts exhibited significantly enhanced selectivity to  $\text{CO}_2$ . In contrast, the catalytic performance in chlorobenzene oxidation was increasing with increasing noble metal content. The positive effect of noble metal addition was ascribed to the oxidation of chlorine species, which block the active sites, by noble metals. In ethanol oxidation, the catalytic performance increased linearly with increasing Pt content and the influence of Pt loading on the mechanism of ethanol oxidation was revealed, while the introduction of gold had only a minor effect. Finally in toluene oxidation, only platinum catalysts with 0.35 wt. % and higher loading exhibited better catalytic performance than the pure support.

### Acknowledgement

The financial support of Grant Agency of the Czech Republic (project 13-24186P) is appreciated.