



národní
úložiště
šedé
literatury

Progress in Helicene Stationary Phases

Cerhová, Marie
2015

Dostupný z <http://www.nusl.cz/ntk/nusl-188306>

Dílo je chráněno podle autorského zákona č. 121/2000 Sb.

Tento dokument byl stažen z Národního úložiště šedé literatury (NUŠL).

Datum stažení: 02.06.2024

Další dokumenty můžete najít prostřednictvím vyhledávacího rozhraní nusl.cz.

Preparation of Nanocrystalline Titania Thin Films by Using Pure and Modified Supercritical Carbon Dioxide

Student: Ing. Marie Cerhová

Supervisor: Ing. Marie Sajfrová, PhD.

Supervising Expert: Ing. Lenka Matějová, PhD.

Titania films are materials of great interest, as TiO_2 anatase crystal structure shows a high photocatalytic activity, chemical stability, strong oxidation activity, and non-toxicity. Anatase can be used in environmental applications, such as air- and water-purification¹ or for the decomposition of organic compounds.² The photocatalytic efficiency of thin films depends not only on their phase composition but also on hydrophilicity, specific surface area, crystallinity and crystallite-size. These properties can be significantly influenced by the preparation method used.

The commonly applied method for the preparation of pure and crystalline TiO_2 thin films is calcination.³ Nevertheless, this thermal treatment presents some disadvantages, such as recrystallization, excessive sintering, crystallite growth, and a decrease in the specific surface area. Furthermore, the properties or photocatalytic performance cannot be easily controlled.

Therefore, calcination has been combined with supercritical fluid extraction (SFE) or pressurized liquid extraction (PLE). It was found that the pre-treatment using supercritical carbon dioxide (scCO_2) proposed for lowering the process temperature of sol-gel derived metal oxide film helps to increase the thermal stability and photocatalytic activity of films.⁴

The motivation of this work is to utilize the SFE for the direct preparation of highly pure TiO_2 thin films without any subsequent thermal processing. Extraction with pure and modified scCO_2 was tested and compared with PLE. Different types of liquid solvents (water, ethanol, acetone etc.) were used as scCO_2 modifiers at concentrations from 0 to 30 mass %. The effect of extraction temperature (40–150 °C), pressure (10–65 MPa) and the volume (50–200 g) and flow rate (0.3–1.8 g/min) of solvents passed through the extractor on microstructure and purity of TiO_2 thin films were examined.

The prepared thin films were characterized with respect to the (micro)structural properties by Raman spectroscopy. The most promising

thin films were analyzed by means of X-ray diffraction to determine the crystallite size, the phase composition, and the film thicknesses. The contact angles of films were measured to obtain the information about surface wettability.

When pure scCO_2 or pressurized hot water was used as the solvent no crystallization occurred. The addition of a small amount of water to scCO_2 at optimum extraction conditions ($T=150\text{ }^\circ\text{C}$, $p=30\text{ MPa}$) led to the direct crystallization of films. The modification of scCO_2 by organic solvents resulted in the removal of organic precursors and thus in the increase of the TiO_2 thin film purity. When SFE was terminated by pure scCO_2 drying, the crystal size of 12 nm was achieved.

References

1. Sökmen M. et al. *J. Photochem. Photobiol. A: Chem.* **2002**, 147, 77–81.
2. Andersson M. et al. *J. Phys. Chem. B* **2002**, 106, 10674–10679.
3. Wang Y.-D. et al. *J. Non-Cryst. Solid.* **2003**, 319, 109–116.
4. Wei M. et al. *J. Mater. Chem.* **2007**, 17, 3888–3893.