



národní  
úložiště  
šedé  
literatury

**The Effect of Experimental Design on Crystal Size of TiO<sub>2</sub> Thin Films Prepared by Using Modified Supercritical Carbon Dioxide.**

Cerhová, Marie  
2016

Dostupný z <http://www.nusl.cz/ntk/nusl-254032>

Dílo je chráněno podle autorského zákona č. 121/2000 Sb.

Tento dokument byl stažen z Národního úložiště šedé literatury (NUŠL).

Datum stažení: 08.05.2024

Další dokumenty můžete najít prostřednictvím vyhledávacího rozhraní [nusl.cz](http://nusl.cz).

## The effect of experimental design on crystal size of TiO<sub>2</sub> thin films prepared by using modified supercritical carbon dioxide

M. Cerhová, M. Sajfrtová, <sup>1</sup>L. Matějová, V. Dřínek, <sup>2</sup>S. Daniš, V. Jandová

Institute of Chemical Process Fundamentals of the ACS, v.v.i., Rozvojová 135, 165 02 Prague 6, Czech Republic, [cerhova@icpf.cas.cz](mailto:cerhova@icpf.cas.cz); <sup>1</sup>Institute of Environmental Technology, VŠB-Technical University of Ostrava, 17.listopadu 15/2172, 708 33 Ostrava – Poruba, Czech Republic; <sup>2</sup>Department of Condensed Matter Physics, Faculty of Mathematics and Physics, Charles University in Prague, Ke Karlovu 5, 121 16 Prague 2, Czech Republic

TiO<sub>2</sub> is known as an efficient photocatalyst for its good ability to produce the pairs electron-hole under UV light [1]. Moreover, titania exhibits high chemical stability, strong oxidative activity and non-toxicity. It has been investigated in a form of thin films in many application areas; as sensing films of gas sensors [2], coatings for self-cleaning surfaces [3], photocatalyst promising in water- and air-purification [4] or degradation of organic pollutants [5].

Properties as phase composition, crystallinity or crystallite-size influencing the photocatalytic activity and are size dependent. That means the controlled preparation of nanocrystallites is important for their applications. Calcination is a commonly used method for the purification and to crystallize TiO<sub>2</sub> thin films [6]. Unfortunately, this thermal treatment is accompanied by excessive sinteration, crystallite growth or recrystallization. To reduce the process temperature and to increase the thermal stability and the photocatalytic activity the TiO<sub>2</sub> thin films can be also extracted by scCO<sub>2</sub>, subcritical water or pressurized organic solvents [7].

In this work, the method using pure and modified supercritical carbon dioxide was tested to prepare a set of crystalline TiO<sub>2</sub> thin films deposited on soda-lime glass. Precursor solution for TiO<sub>2</sub> films was prepared by a templated sol-gel method in the reverse micelle environment. Simple approach or combination of several steps performed at different temperature (40-150 °C) and solvent composition was applied at pressure 30 MPa. Water, ethanol and water : ethanol (1:1) mixture were added into supercritical CO<sub>2</sub> as modifiers at concentration 10-30 wt.%. The effect of extraction design on microstructure and purity of TiO<sub>2</sub> thin films were examined.

The thin films were characterized with respect to the (micro)structural properties by Raman spectroscopy. The most promising thin films samples were analyzed by means of X-ray diffraction to determine the crystallite size and the phase composition.

TiO<sub>2</sub> thin films treated by water modified scCO<sub>2</sub> exhibited the crystalline structure anatase. Subsequent modification of scCO<sub>2</sub> by 10 wt. % ethanol led to the removal of the organic precursor used in the sol-gel method and thus to increase the purity of TiO<sub>2</sub> thin films. The additional drying with 200 g of pure scCO<sub>2</sub> had no positive effect on crystal growth but the mixture of anatase and brookite crystals was formed. At the optimal conditions of SFC by water : ethanol (1:1) mixture modified scCO<sub>2</sub> (30 MPa, 150 °C, 100 g of scCO<sub>2</sub>) the anatase crystals with the size of 13 nm were obtained.

Acknowledgements. The financial support of the Grant Agency of the Czech Republic (projectno.14-23274S) is gratefully acknowledged.

[1] Prieto O. et al. *Sol. Energy*. **2005**, *79*, 376-383. [2] Savage N. O. et al. *Sens. Act. B*. **2001**, *72*, 239-248. [3] Fujishima A. et al. *Electrochim. Acta*. **2000**, *45*, 4683–4690. [4] Hsien Y.-H. et al. *Appl. Catal. B: Environ.* **2001**, *31*, 241–249. [5] Nakata K. et al. *Electrochim. Acta*. **2012**, *84*, 103. [6] Zhou M. et al. *J. Hazard. Mat.* **2008**, *154*, 1141–1148. [7] Matejova L. et al., EMSF 2014, Marseille, France, p.161 (Full text on Flash disc).