



národní
úložiště
šedé
literatury

Silicon Nanowire with a Complex Structure.

Dřínek, Vladislav
2016

Dostupný z <http://www.nusl.cz/ntk/nusl-260857>

Dílo je chráněno podle autorského zákona č. 121/2000 Sb.

Tento dokument byl stažen z Národního úložiště šedé literatury (NUŠL).

Datum stažení: 08.05.2024

Další dokumenty můžete najít prostřednictvím vyhledávacího rozhraní nusl.cz .

Silicon nanowire with a complex structure

V. Dřínek^{1*}, J. Kupčík²

¹ Institute of Chemical Process Fundamentals ASCR, Rozvojová 135, 165 02 Prague 6, CZ

² Institute of Inorganic Chemistry ASCR, Řež u Prahy 100, 250 68, Czech Republic

* The corresponding author e-mail: drinek@icpf.cas.cz

Keywords: nanowire, silicon, nanocrystalline

Nowadays a continual growing demand for green energy production, smart grids, energy storage, electric vehicles etc. boosts up a need for new technology approaches. One of the solutions is conversion of the solar energy into various forms of energy mostly chemical bond or electric energy.

At this moment, silicon seems to be the best choice for the sunlight absorbing materials. Nevertheless, indirect bandgap of crystalline silicon and relatively low conductivity of amorphous silicon are the great disadvantage in construction of photovoltaic devices. We hope that prepared silicon nanowires (SiNWs) with a complex structure allow a solution of such challenge.

SiNWs long up to 10 μm and thick about 100 nm were synthesized using silane as a precursor by means of CVD technique at 500 °C on molybdenum or stainless steel substrates in a quartz tube placed in a furnace. Transmission Electron Microscopy showed that the jacket consists of nanocrystal of size 1–2 nm. Thin crystalline core thick ~ 10 nm grew in $\langle 110 \rangle$ direction. It is commonly recognized that very small silicon nanocrystals having size less than 5 nm are governed by quantum size effects; for example their indirect bandgap merges into a direct one (Fig.).




Figure: Quantum size phenomenon for semiconductor with indirect bandgap [1]

Reference

[1] J. Dian, I. Jelínek, *Chem. listy*, **104**, 770–777 (2010)

Acknowledgments

This work was supported by the Grant Agency of the Czech Republic (grant No. 15-08842J).