



národní  
úložiště  
šedé  
literatury

## **Inhibitive Effect of Pyridine and Toluene on HDS of Thiophene over Mo/Al<sub>2</sub>O<sub>3</sub> Based Catalysts**

Gulková, Daniela  
2011

Dostupný z <http://www.nusl.cz/ntk/nusl-81046>

Dílo je chráněno podle autorského zákona č. 121/2000 Sb.

Tento dokument byl stažen z Národního úložiště šedé literatury (NUŠL).

Datum stažení: 05.05.2024

Další dokumenty můžete najít prostřednictvím vyhledávacího rozhraní [nusl.cz](http://nusl.cz) .

# INHIBITIVE EFFECT OF PYRIDINE AND TOLUENE ON HDS OF THIOPHENE OVER Mo/Al<sub>2</sub>O<sub>3</sub> BASED CATALYSTS

Daniela Gulková and Zdeněk Vít

*Institute of Chemical Process Fundamentals of the AS CR, v. v. i.,  
Rožnovská 135, 165 02 Prague 6, Czech Republic*

Hydrodesulfurization (HDS) carried out on conventional CoMo/Al<sub>2</sub>O<sub>3</sub> sulfide catalysts is known to be strongly inhibited by nitrogen heterocycles and polyaromatic compounds [1]. This undesirable effect, reducing efficiency of catalysts, can be influenced by different factors, related to the composition of catalysts, type and amount of the inhibitor and the way of its adsorption. Recently, we observed that Mo/Al<sub>2</sub>O<sub>3</sub> sulfide catalyst promoted by Rh showed in thiophene HDS much better tolerance to the presence of pyridine than CoMo/Al<sub>2</sub>O<sub>3</sub>. It was proposed this was mainly due to the higher C-N bond cleavage activity of the Rh promoted catalyst, which facilitated the removal of inhibitor by hydrodenitrogenation [2]. Pyridine is nitrogen compound possessing both basic and aromatic character. In order to get more information concerning possible role of the aromatic ring in such inhibition, part of experiments was also performed with addition of toluene. Toluene was chosen because of similar molecular size to pyridine and non-basic character. The aim was to compare the inhibitive effects of pyridine and toluene on thiophene HDS over Mo/Al<sub>2</sub>O<sub>3</sub> catalysts promoted by Co and Rh.

The catalysts contained 9 % Mo and 2.4 % Co (or 0.36 % Rh). The Rh promoted catalyst was prepared by impregnation of sulfided Mo/Al<sub>2</sub>O<sub>3</sub> by Rh acetylacetonate. Catalysts were sulfided by 10 % H<sub>2</sub>S/H<sub>2</sub> at 400°C/1h. The HDS was carried out at 320°C and 20 bar in an integral flow reactor. The feed contained either thiophene or mixture of thiophene and pyridine (or thiophene and toluene).

It was found that HDS activities of Mo and CoMo catalysts were strongly inhibited by pyridine and activity of RhMo catalyst was inhibited less. On the other hand, suppression of HDS by toluene over Mo catalyst was very small and no suppression by toluene was observed over the promoted CoMo and RhMo catalysts. This suggests that aromatic character of inhibitor does not play an important role and the inhibition of thiophene HDS by pyridine is caused by its basicity, leading to strong pyridine adsorption on catalytic sites through nitrogen atom.

## Acknowledgement

The financial support of the Czech Science Foundation (grant 104/09/0751) is gratefully acknowledged.

## References:

- 1 Topsoe, H.; Clausen, B.S.; Massoth, F.E.; in: J.R. Anderson and M. Boudart (Eds.), *Hydrotreating Catalysts*, Science and Technology, Springer, 1996, Vol. 11.
- 2 Vít, Z.; Kaluža, L.; Gulková, D.; Top. Catal., 2011, in press.

*Abo Aka*

Oxidative frequent sacchari

While the chain sh CIO. The

The pro compou industry

Despite and puri presence

The wor the react distribut conditior

The rea Typically higher a highly d 5-10%. reproduc

Aknowl The auth Innovativ no. 363/3 activities (2000-20

Referenc

1 Rulf, O

2 Stapley,

3 Hourdir

4 Pezzair