



národní  
úložiště  
šedé  
literatury

## **Mesoporous Silica-Alumina Modified by Acid Extraction as Support of Pd and Pd-Pt Catalysts in HDS of Model Compounds**

Vít, Zdeněk  
2011

Dostupný z <http://www.nusl.cz/ntk/nusl-81048>

Dílo je chráněno podle autorského zákona č. 121/2000 Sb.

Tento dokument byl stažen z Národního úložiště šedé literatury (NUŠL).

Datum stažení: 05.05.2024

Další dokumenty můžete najít prostřednictvím vyhledávacího rozhraní [nusl.cz](http://nusl.cz).

MESOPOROUS SILICA-ALUMINA MODIFIED BY ACID EXTRACTION  
AS SUPPORT OF Pd AND Pd-Pt CATALYSTS IN HDS  
OF MODEL COMPOUNDS

Zdeněk Vít, Hana Kmentová, Daniela Gulková and Luděk Kaluža

*Institute of Chemical Process Fundamentals of the ASCR, v.v.i.,  
Rožvojová 135, 165 02 Prague 6, Czech Republic*

Mesoporous silica-aluminas (MSA) are often studied as supports of catalysis for hydrodesulfurization (HDS) because of large surface areas, suitable porosity and acidity. Recently, we synthesized a MSA containing 50 % alumina by co-gelation [1]. This carrier has further been modified by extraction of the alumina phase by  $\text{HNO}_3$  in order to increase its acidity. Pt catalysts prepared from such modified support showed substantially higher HDS activity [2]. Similar positive effect was also observed in the case of Pd catalysts [3]. The effect of acid extraction on the properties of MSA support and on activity of Pd and Pd-Pt catalysts is subject of this work.

A new batch of MSA contained 52 % alumina (MSA52). Part of MSA was extracted by 1 N  $\text{HNO}_3$  at 75°C/2 h and calcined at 400°C. The product contained 9 % alumina (MSA9). Both supports were characterized by  $\text{N}_2$  adsorption, Hg porosimetry,  $^{27}\text{Al}$  MAS NMR and by tests in cyclohexene isomerization and cumene cracking. The catalysts were prepared by impregnation of supports with  $\text{Pd}(\text{CH}_3\text{COO})_2$ ,  $\text{Pd}(\text{NH}_3)_4\text{Cl}_2$  and  $\text{Pt}(\text{NH}_3)_4(\text{OH})_2$ . The bimetallic Pd-Pt catalyst was prepared by co-impregnation. Catalysts were reduced by  $\text{H}_2$  at 400°C. A CoMo/alumina catalyst was sulfided with 10 %  $\text{H}_2\text{S}$  in  $\text{H}_2$  at 400°C. The activities of catalysts were tested in HDS of thiophene and benzothiophene.

Extraction of MSA52 diminished the alumina content to 9 % and increased the BET area and isomerization and cracking activities. This was ascribed to partial removal of the non-acidic  $\text{Al}_{\text{ox}}$  species and unblocking of the strong acidic sites of silica-alumina, associated with the  $\text{Al}_{\text{w}}$  species. Higher acidity and surface area of the MSA9 improved the activities of Pd catalysts in HDS of thiophene and benzothiophene. The bimetallic Pd-Pt catalyst prepared from MSA9 showed highest HDS activity.

**Acknowledgement**

The financial support of the Czech Science Foundation (grants 104/09/0751 and P106/11/0902) is acknowledged.

**References:**

- <sup>1</sup> Vít, Z., Šolcová, O.; *Micropor. Mesopor. Mater.* **2006**, *96*, 197.
- <sup>2</sup> Vít, Z., Gulková, D.; Kaluža, L.; Bakardjeva, S.; Boaro, M.; *Appl. Catal. B: Environ.*, **2010**, *100*, 463.
- <sup>3</sup> Vít, Z.; Kmentová, H.; Kaluža, L.; Gulková, D.; Boaro, M.; *Appl. Catal. B: Environ.*, **2011**, in press.

DEV  
LO

Resea  
and

Introd  
Requi  
must b  
more i  
conten  
cataly  
suitabl  
assess  
term a  
highly  
The ai  
which  
(e.g. 1  
Princ  
The pr  
varyin  
Deacti  
pressur  
catalys  
Result  
It has t  
(in sh  
sulfur c  
ppm be  
deactiv  
product  
after a  
quickly  
Conclu  
By a s  
signifi  
more cc  
Ackno  
The fin  
(project  
connects  
Fund an